

Attorney Docket No. 81756.0005  
Patent Application No. 10/090,597

This listing of claims will replace all prior versions, and listings, of claims in the application:

Listing of Claims:

1.-13. (Cancelled)

14. (Currently Amended) A method for manufacturing an electroluminescent element comprising:

forming a first electrode group by a predetermined arrangement of a plurality of first electrodes on a substrate;

forming a bank group by a predetermined arrangement of a plurality of banks intersecting with the first electrode group;

forming an electroluminescent material layer ~~by filing the electroluminescent material~~ in between banks with liquid material such that at least a bottom region between the banks is filled with the liquid material ~~by means of an ink jet method;~~  
and

forming a second electrode group separated by the banks by depositing a second electrode material onto the electroluminescent material layer.

15. (Previously Presented) The method according to claim 14, wherein the banks are formed such that an angle between side faces thereof and a face on which the banks are installed is a right angle, and the second electrode group is formed by depositing the second electrode material by oblique vapor deposition from a direction confronting the side faces, or a direction perpendicular to the vertical direction of the banks.

COPY

Attorney Docket No. 81756.0005  
Patent Application No. 10/090,597

16. (Previously Presented) The method according to claim 14, wherein the banks are formed such that an angle between at least one side face of the banks and a face on which the banks are installed is an acute angle, and the second electrode group is formed by depositing the second electrode material by oblique vapor deposition from a direction confronting the side face or a vertical direction of the banks.

17. (Previously Presented) The method according to claim 14, wherein the banks are formed such that an angle between at least one side face of the banks and a top face thereof is an acute angle, and the second electrode group is formed by vapor deposition from a vertical direction of the banks.

18. (Currently Amended) The method according to claim 14, wherein at least one of non-glare treatment and/or antireflection treatment is carried out on a surface of the electroluminescent element.

19. (Previously Presented) The method according to claim 14, wherein the predetermined arrangement is a parallel arrangement.

20. (Previously Presented) The method according to claim 19, wherein the banks are formed such that an angle between side faces thereof and a face on which the banks are installed is a right angle, and the second electrode group is formed by depositing the second electrode material by oblique vapor deposition from a direction confronting the side faces, or a direction perpendicular to the vertical direction of the banks.

COPY

Attorney Docket No. 81756.0005  
Patent Application No. 10/090,597

21. (Previously Presented) The method according to claim 19, wherein the banks are formed such that an angle between at least one side face of the banks and a face on which the banks are installed is an acute angle, and the second electrode group is formed by depositing the second electrode material by oblique vapor deposition from a direction confronting the side face or a vertical direction of the banks.

22. (Previously Presented) The method according to claim 19, wherein the banks are formed such that an angle between at least one side face of the banks and a top face thereof is an acute angle, and the second electrode group is formed by vapor deposition from a vertical direction of the banks.

23. (Currently Amended) The method according to claim 19, wherein at least one of non-glare treatment ~~and/or~~ antireflection treatment is carried out on a surface of the electroluminescent element.

24. (Previously Presented) The method according to claim 14, wherein the predetermined arrangement is a line arrangement.